

TUNGSTEN TITANIUM CARBIDE (HIGH VACUUM 100/300)

Description of Product The WTiC is the most important mixed carbide of the cemented carbides. The area of application for WTiC is the production of hardmetal mixtures. This product is used for the manufacture of cemented carbide products.

Grades Available

Product Designation
50/50 HV 100
50/50 HV 300
70/30 HV 100
70/30 HV 300

Chemical Characteristics¹⁾

(Mass fraction in % [cg/g]; ppm [µg/g])

	(W, Ti)C 50/50 HV 100 / HV 300	(W, Ti)C 70/30 HV 100 / HV 300
W	46.0 - 47.0 %	64.7 - 66.0 %
Ti	39.6 - 40.5 %	23.0 - 24.6 %
C _{total}	12.4 - 13.1 %	9.5 - 10.2 %
C _{free}	max. 0.3 %	max. 0.4 %
C _{combined}	min. 12.1 %	min. 9.1 %
O (HV 100)	max. 0.5 %	max. 0.5 %
O (HV 300)	max. 0.2 %	max. 0.2 %
N	max. 1500 ppm	max. 1500 ppm
Ca	max. 100 ppm	max. 100 ppm
Fe	max. 800 ppm	max. 600 ppm
Na + K	max. 50 ppm	max. 50 ppm
Si	max. 200 ppm	max. 200 ppm

If required, the information on the solid solution can be confirmed by x-ray diffraction.

Physical Characteristics

Grades	Fisher number (as supplied)
50/50 HV 100	0.9 - 1.3 µm
50/50 HV 300	2.5 - 3.5 µm
70/30 HV 100	0.9 - 1.3 µm
70/30 HV 300	2.5 - 3.5 µm

1) Information on chemical analytical methods and list of analyzed items on request.

Packaging Standard Packaging:
50 kg in 30 l steel drums with a polyethylene bag

Other kinds of packaging are available on request.

Storage and Handling Storage and handling are subject to the rules and regulations in the country of use.

Hazards identification in Advertising (REGULATION (EC) No 1272/2008 Article 48)
None.

Documentation An inspection document in accordance with EN 10204 is supplied with every shipment.

Höganäs Germany GmbH

Im Schleeke 78-91
38642 Goslar/Germany

Säckinger Straße 51
79725 Laufenburg/Germany

<https://www.hoganas.com/en/contact/>

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Höganäs Germany GmbH. All information is given without warranty or guarantee. It is expressly understood and agreed that the customer assumes and hereby expressly releases Höganäs Germany GmbH from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Höganäs Germany GmbH. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. In case of order please refer to issue number of the respective product data sheet. All deliveries are based on the latest issue of the product data sheet and the latest version of our General Conditions of Sale and Delivery